

PLUTUS HEAT TRANSFER OIL

Product Description:

Plutus Heat Transfer Oil is premium heat transfer oil designed to give outstanding service in a variety of applications. Plutus Heat Transfer Oil is blended from highly refined hydro-treated base oil and fortified with oxidation inhibitors to enhance high temperature performance and stability. Plutus Heat Transfer Oil is resistant to oxidation and high temperature degradation, giving this fluid a long usable life and minimizing deposit formation that can be inhibit efficient heat transfer.

Plutus Heat Transfer Oil may be used in both open and inert gas blanketed close heat transfer systems. The maximum temperature for use in an open system shall not exceed 150°C at the point where the oil is exposed to the air. In closed, inert gas blanketed systems, Hydropure Plutus Heat Transfer Oil can be used up to 320°C.

Applications / Benefits:

- Blended with naturally high VI base oils.
- Contains high temperature oxidation inhibitors.
- Minimizes deposit formation.
- Long fluid life.

Typical Characteristics:

Test Description	Method	22	32	46	68	100
ISO Viscosity Grade	-	22	32	46	68	100
Specific Gravity @ 15 °C	ASTM D 4052	0.854	0.863	0.869	0.872	0.873
Flash Point, °C	ASTM D 92	210	220	225	228	238
Pour Point, °C	ASTM D 97	-24	-24	-21	-18	-18
Kinematic Viscosity, cSt @ 40°C	ASTM D 445	22	32	46	68	100
cSt @ 100°C	ASTM D 445	4.47	5.34	6.69	8.61	11.3
Viscosity Index	ASTM D 2270	115	98	97	97	98
Color	ASTM D 1500	<0.5	<0.5	<0.5	<0.5	<0.5

Specific Heat Capacity

Temperature, °C	25	100	150	200	250	300
ISO 22 Specific Heat Capacity, kJ/kg·°C	1.82	2.08	2.21	2.49	2.73	2.91
ISO 32 Specific Heat Capacity, kJ/kg·°C	1.89	2.17	2.33	2.51	2.72	2.88
ISO 46 Specific Heat Capacity, kJ/kg·°C	1.95	2.21	2.36	2.52	2.7	2.87
ISO 68 Specific Heat Capacity, kJ/kg·°C	1.97	2.24	2.41	2.53	2.67	2.85
ISO 100 Specific Heat Capacity, kJ/kg·°C	1.99	2.27	2.45	2.55	2.65	2.82

Max. Film Temperature, °C	340
Max. Bulk Temperature, °C	320

Issued by HPURE Lubricant SG Tel: +65 6861 1157 www.hpure-lube.com

Furnishing the information contained does not constitute a representation by HPURE Lubricants that any product or process is free from patent infringement claims of any 3rd party nor does it constitute the granting of a license under any patent of HPURE Lubricants or any 3rd party. HPURE Lubricants assumes no liability for any infringement which might arise out of the use of the product. The information and suggestions for use & application presented herein represent the best information available to us and are believed to be reliable. They should not, however, be construed as controlling suggestions, and users are urged to conduct confirmatory test to determine final suitability for their specific end users. HPURE Lubricants warranty only that its products meet the specifications which it sets for them and specifically DISCLAIMS ALL OTHER WARRANTIES relating to the products and the application thereof, EXPRESS or IMPLIED

including and not limited to warranties of MERCHANTABILITY and FITNESS.